

ExxonMobil

Somentor™ rolling oils

Energy lives here



North America

ExxonMobil's Somentor™ hydrocarbon fluids meet the safety and performance standards required by the aluminum industry and have been widely used for more than two decades.

Key attributes

- improved annealing properties, thereby reducing the potential of production rejects
- suitable for rolling of alloys used for food packaging
- very low aromatic content
- low odor

Somentor™ fluids are manufactured under Good Manufacturing Practices and meet the FDA 21 chapter 178.3910 (a) and (b) regulations¹.

To formulate and optimize rolling oils that meet the needs of individual mill operations, Somentor™ fluids are generally blended with additives, including the Mobil™ line of Wyrol™ roll oil additives.

Somentor™ grades are available for direct purchase from your ExxonMobil sales representative or via our network of regional distributors with local storage capabilities.

Somentor 29

- low viscosity, well suited for aluminum foil rolling or as a separation fluid for foil doubling
- narrow typical distillation range, resulting in more consistent viscosity through the process

Somentor 34 and Somentor 35

- higher viscosity
- unique distillation ranges suited for the needs of aluminum sheet rolling mills
- high flash points for severe operating conditions inherent in aluminum sheet rolling, lowering fire risk during strip breakage
- high molecular weight and heat capacity that may boost cleaning / heat transfer efficiency

¹ This brochure is not the official source for regulatory claims. For regulatory compliance statements, please contact Customer Service. For other information, please contact your sales representative.

Select the product that is best suited to your requirements from our range of available Somentor™ rolling oils.



Key sales specifications	Method	Somentor 29	Somentor 34	Somentor 35	Unit
Aromatics content (max)	AMS 140.31 UV1 ²	0.2	0.5	0.5	wt%
Flash point (min)	ASTM D93	77	101	105	°C
Distillation range	ASTM D86				°C
Initial boiling point (min)		200	230	237	
Dry point (max)		248		277	
Final boiling point (max)			270		
Key typical values	Method	Somentor 29	Somentor 34	Somentor 35	Unit
Distillation range	ASTM D86				°C
Initial boiling point		207	236	248	
Dry point		237		269	
Final boiling point			265		
Viscosity at 25°C	ASTM D445 calculated	2.21	2.50	3.59	cSt
Viscosity at 40°C	ASTM D445	1.66	2.20	2.57	cSt

Note: The number of significant figures shown in the table above may differ versus the requirements stated in the test method.

² Details available upon request



©2016 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.