

# Vistamaxx™ Performance Polymer 8580

## Propylene Elastomer

## 产品说明

Vistamaxx™ 8580 performance polymer is primarily composed of isotactic propylene repeat units with random ethylene distribution, and is produced using ExxonMobil's proprietary metallocene catalyst technology. It has very low viscosity that enables its use in hot melt adhesives (HMAs) and as a process aid or viscosity modifier in extrusion and injection molding applications providing enhanced flow characteristics that can lead to efficiency and cycle time improvements. It is available in pellet form.

## 关键特性

- Low density
- Very low viscosity
- Low odor and low color
- Non-corrosive

## 总览

供货地区 <sup>1</sup>	▪ 北美洲 ▪ 非洲和中东	▪ 拉丁美洲 ▪ 欧洲	▪ 亚太地区
应用	▪ 聚合物改性	▪ 热熔胶	
用途	▪ 混料	▪ 粘合剂	
形式	▪ 粒子		
加工方法	▪ 复合	▪ 挤出	▪ 注射成型
修订日期	▪ 07/25/2024		

## 物理性能

	典型数值 (英制)	典型数值 (公制)	测试方法
密度 <sup>2</sup>	0.870 g/cm <sup>3</sup>	0.870 g/cm <sup>3</sup>	ExxonMobil Method
乙烯成份	10 wt%	10 wt%	ExxonMobil Method
粘度 @ 374° F (190° C) <sup>2</sup>	4380 cP	4380 mPa · s	ExxonMobil Method

## 硬度

	典型数值 (英制)	典型数值 (公制)	测试方法
肖氏硬度 (邵氏 C)	21	21	ExxonMobil Method

## 机械性能

	典型数值 (英制)	典型数值 (公制)	测试方法
拉伸断裂强度	580 psi	4.0 MPa	ExxonMobil Method
拉伸应力 (在 100% 时)	280 psi	1.9 MPa	ExxonMobil Method
伸长率 (在断裂伸长时)	1006 %	1006 %	ExxonMobil Method

## 热性能

	典型数值 (英制)	典型数值 (公制)	测试方法
熔融温度	196 ° F	91 ° C	ExxonMobil Method
玻璃化, T <sub>g</sub>	-20 ° F	-29 ° C	ExxonMobil Method

## 补充信息

For handling and safety information, consult the appropriate Safety Data Sheet.

ExxonMobil Test Methods, some of which were developed from ASTM test methods, are available upon request.

It is the responsibility of the user to ensure that the composition containing our product meets the limitations of relevant regulations. Please contact Customer Service for the official food law certificates which provide more detailed information.

## 法律声明

未经埃克森美孚化工书面允许，本产品，包括其产品名称，不得在任何医疗应用领域予以使用或进行测试。更多详情，请咨询您当地的客服代表。

## Vistamaxx™ Performance Polymer 8580 Propylene Elastomer

### 加工说明

Vistamaxx polymers have a wide temperature processing window. A good starting point for temperatures is 10° C above the highest melting point. This material does not require drying and can be compounded or used in a dry blend. Use conventional processing knowledge to ensure mixing of the materials.

### 备注

典型数值：此等典型数值不应被解释为规格。

<sup>1</sup> 在所标识的可供应区域的一个或多个国家/地区中可能无法供应此产品。请联系您的销售代表以获取完整的可供应国家/地区列表

<sup>2</sup> Property specified in conventional unit of measure.

### 标准免责声明中文译文 [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2025 埃克森美孚。埃克森美孚（ExxonMobil），埃克森美孚的徽标（ExxonMobil logo）及连接的“X”设计和在本文档中使用的所有其他商品或服务名称，除非另有标明，否则均为埃克森美孚的商标。未经埃克森美孚的事先书面授权，不得分发、展示、复印或改变本文档。使用者可在埃克森美孚授权的范围内，分发、展示和/或复印本文档，但必须毫无改动并保持其完整性，包括所有的页眉、脚注、免责声明及其他信息。使用者不可将本文档全文或部份复制到任何网站。埃克森美孚不保证典型（或其它）数值。本文档包含的所有数据是基于代表性样品的分析，而不是实际运送的产品。本文档所含信息仅是所指明的产品或材料未与任何其它产品或材料结合使用时的相关信息。我们的信息基于收集之日被认为可靠的数据，但是，我们并不明示或暗示地陈述、担保或以其它方式保证此信息或所描述产品、材料或工艺的适销性、适宜于某一特定用途、不侵犯专利权、适用性、准确性、可靠性或完整性。使用者对在其感兴趣的领域使用该材料、产品或工艺所做的一切决定负全部责任。我们明确声明将不对由于任何人使用或依赖本文档所含任何信息而导致的或与此相关的直接或间接遭受或者产生的任何损失、损害或伤害承担责任。本文档不应视作我们对任何非埃克森美孚产品或工艺的认可，并且我们明确否认任何相反的含意。“我们”、“我们的”、“埃克森美孚化工”“埃克森美孚产品方案业务”等词语均为方便而使用，埃克森美孚产品方案业务公司、埃克森美孚公司，或由它们直接或间接控制的任何关联公司中的一家或者多家。

[exxonmobilchemical.com](http://exxonmobilchemical.com)